



Date:- 14th September, 2018

Issue: 1

An application note on wearout failure mechanisms

In general, the overall reliability of power semiconductor devices is represented by the “bathtub” curve shown in figure 1. The wearout phase of a device is linked to the general accumulation of physical damage under the operating load conditions in the application. The main changes in the properties of the device are linked to mechanical wear out due to the differences in the thermal expansion coefficients of the components in the housing. The surface of the die can show significant “scrubbing” due to expansion and contraction of the components. The scrubbing may lead to the formation of intermetallic compounds at these component interfaces as shown in figures 2-4. The build-up can then lead to changes in the on-state, V_T or forward voltage, V_F characteristic and in addition changes in the junction leakage current over long periods of time.

It is difficult to provide actual quantitative values to the X axis as this will depend very much on the conditions in the application. However, for many applications it is prudent to consider a refurbishment program after around thirty years’ service.

Generally, it is not good practice to remove a device from an assembly and then re-mount that device back into the same assembly using the same components. The device is unlikely to be re-located in exactly the same orientation in the clamp assembly, so the contact of the components is likely to be compromised due to the extended time in service.




Figure 1: Typical "bathtub" curve



Figure 2: Initial evidence of thermal cycling scrubbing at the edge on the cathode contact area



Figure 3: Initial evidence of thermal cycling scrubbing on the anode molybdenum contact



Figure 4: More extensive evidence of thermal cycling scrubbing at the edge on the cathode contact area

Important Notice:

This document is provided by Littelfuse, Inc. ("Littelfuse") for informational and guideline purposes only. Littelfuse assumes no liability for errors or omissions in this document or for any of the information contained herein. Information is provided on an "as is" and "with all faults" basis for evaluation purposes only. Applications described are for illustrative purposes only and Littelfuse makes no representation that such applications will be suitable for the customer's specific use without further testing or modification. Littelfuse expressly disclaims all warranties, whether express, implied or statutory, including but not limited to the implied warranties of merchantability and fitness for a particular purpose, and non-infringement. It is the customer's sole responsibility to determine suitability for a particular system or use based on their own performance criteria, conditions, specific application, compatibility with other components, and environmental conditions. Customers must independently provide appropriate design and operating safeguards to minimize any risks associated with their applications and products.

LITTELFUSE PRODUCTS ARE NOT DESIGNED FOR, AND SHALL NOT BE USED FOR, ANY PURPOSE (INCLUDING, WITHOUT LIMITATION, AUTOMOTIVE, MILITARY, AEROSPACE, MEDICAL, LIFE-SAVING, LIFE-SUSTAINING OR NUCLEAR FACILITY APPLICATIONS, DEVICES INTENDED FOR SURGICAL IMPLANT INTO THE BODY, OR ANY OTHER APPLICATION IN WHICH THE FAILURE OR LACK OF DESIRED OPERATION OF THE PRODUCT MAY RESULT IN PERSONAL INJURY, DEATH, OR PROPERTY DAMAGE) OTHER THAN THOSE EXPRESSLY SET FORTH IN APPLICABLE LITTELFUSE PRODUCT DOCUMENTATION. WARRANTIES GRANTED BY LITTELFUSE SHALL BE DEEMED VOID FOR PRODUCTS USED FOR ANY PURPOSE NOT EXPRESSLY SET FORTH IN APPLICABLE LITTELFUSE DOCUMENTATION. LITTELFUSE SHALL NOT BE LIABLE FOR ANY CLAIMS OR DAMAGES ARISING OUT OF PRODUCTS USED IN APPLICATIONS NOT EXPRESSLY INTENDED BY LITTELFUSE AS SET FORTH IN APPLICABLE LITTELFUSE DOCUMENTATION.